

Declaration of Performance
N°: CELSA01BCN

- Name and identification code:**
Hot rolled products of structural steels, types S235/S275/S355 and grades JR/JO/J2.
- Name and manufacturer's address:**
Compañía Española de Laminación S.L.
C/ Ferralla nº12,
Polígono Industrial San Vicente
S/N
08755 Castellbisbal, Barcelona
(Spain)
- Intended use:**
To be used in welded, bolted and riveted structures.
- System of assessment and verification of constancy of performance of the product**
System 2+
- Notified body:**
AENOR N°0099
Assessment and evaluation of factory production control for the system 2+
Factory production control certificate 0099/CPR/A81/0007, issued on 27th February 2006.

The performances of the product identified in point 1 are in line with the performance declared in point 6.

This declaration of performance is issued in according with Regulation (EU) n° 305/2011, under the sole responsibility of the manufacturer indicated in point 2.

Signed for and on behalf of the manufacturer:



Anders Cardona Pallarès
Quality Manager

Castellbisbal, 14.10.2024

6. Determined performances:

Essential characteristics	Performance						Harmonised technical specifications			
Dimentional and shape tolerances	EN 10056-2		Equal leg angles (L)				EN 10025-1:2004			
	EN 10058		Merchant Rectangular Bars							
	EN 10059		Merchant Squared Bars							
	EN 10060		Merchant Round Bars							
	EN 10024		IPN							
	EN 10034		IPE/HE/UB/UC							
	EN 10279		UPE/UPN/PFC							
Elongation (%)	Type and grade		Nominal thickness (mm)							
			≥3≤40	>40≤63	>63≤100					
	S235JR / JO / J2		26	25	24					
	S275JR / JO / J2		23	22	21					
	S355JR / JO / J2		22	21	20					
Tensile strength (MPa)	Type and grade		Nominal thickness (mm)							
			≥3 ≤100							
	S235JR / JO / J2		360 - 510							
	S275JR / JO / J2		410 - 560							
	S355JR / JO / J2		470 - 630							
Yield strength (MPa)	Type and grade		Nominal thickness (mm)				EN 10025-1:2004			
			≤16	>16≤40	>40≤63	>63≤80			>80≤100	
	S235JR / JO / J2		235	225	215	215			215	
	S275JR / JO / J2		275	265	255	245			235	
	S355JR / JO / J2		355	345	335	325			315	
Impact strength (J)	Type and grade		Temperature (°C)	Nominal thickness ≤150 mm						
	S235/275/355 JR		20	27						
	S235/275/355 JO		0	27						
S235/275/355 J2		-20	27							
Weldability (Chemical Composition)	Type and grade		CEV% max							
			≥3≤40	>30≤40	>40≤150					
	S235JR / JO / J2		0,35	0.35	0,38					
	S275JR / JO / J2		0,40	0.40	0,42					
	S355JR / JO / J2		0,45	0.47	0,47					
Durability (Chemical Composition)	Type and grade		C % max		Si % max	Mn % max	P % max	S % max	N % max	Cu % max
			≤40	>40						
	S235JR		0,19	0,23	---	1,50	0,045	0,045	0,014	0,60
	S235JO		0,19	0,19	---	1,50	0,040	0,040	0,014	0,60
	S235J2		0,19	0,19	---	1,50	0,035	0,035	---	0,60
	S275JR		0,24	0,25	---	1,60	0,045	0,045	0,014	0,60
	S275JO		0,21	0,21	---	1,60	0,040	0,040	0,014	0,60
	S275J2		0,21	0,21	---	1,60	0,035	0,035	---	0,60
	S355JR		0,27	0,27	0,60	1,70	0,045	0,045	0,014	0,60
	S355JO		0,23	0,24	0,60	1,70	0,040	0,040	0,014	0,60
	S355J2		0,23	0,24	0,60	1,70	0,035	0,035	---	0,60